

Aerodur Sealer 42240

Technical Data Sheet

Product Group

Characteristics



Product Information

Components



Specifications



Qualified Product List

Surface Conditions



Surface Preparation/
Cleaning

Instruction for Use



Spray Application (Mix Ratio)



Induction Time



Initial Spraying Viscosity
(23°C/73°F)



Note

Pot life (23°C/73°F)

Specialty Coating

Aerodur Sealer 42240 is a one component polyamide coating used in selective strippable aircraft exterior surface paint schemes.

- Allows topcoats to be stripped with an appropriate and relatively mild paint remover without removing the primary epoxy primer.
- Compatible with various topcoats and basecoat-clearcoat systems.
- When applied in a qualified system it provides resistance to hydraulic fluids and chemicals.

Base	Aerodur® Sealer 42240
Thinner	Thinner 98066

Airbus	AIMS 04-04-032
Airbus	AIMS 04-04-037

Product specifications change constantly, to ensure the most accurate information regarding specifications, please check our online qualified product list (QPL) at aerospace.akzonobel.com/products.

- Check the overcoat times (overcoat window) of the different HS primers with Aerodur Sealer 42240 before application.
- Remove oil, grease and other contaminations prior to application of the sealer.
- Remove dust with e.g. tack rags prior to application of the sealer.

Aerodur Sealer is compatible with the following primers:

- Aerodur LV 2114
- Aerodur HS 2121 CF

	Volume
Aerodur® Sealer 42240	100 parts
Thinner 98066	60 – 80 parts

Allow products to acclimatize to room temperature before use.

- Stir or shake Aerodur Sealer 42240 till all pigment is uniformly dispersed before adding thinner.
- Add Thinner 98066 and stir the mixture thoroughly.

Reduce to spraying viscosity with:
60 – 80 parts - Thinner 98066.

Not applicable.

18 – 24 seconds ISO Cup #4
10 – 13 seconds Zahn Cup #2 Signature series

Viscosity measurements are provided as guidelines only and are not to be used as quality control parameters. Certified information is provided by certification documentation available on request.

16 hours

Aerodur Sealer 42240



Dry Film Thickness (DFT) 8 – 12 μm
0.32 – 0.48 mil

Application Recommendations



Conditions Temperature: 15 – 35 °C
59 – 95 °F
Relative Humidity: 20 – 75 %



Note Aerodur Sealer 42240 may be applied in conditions outside of the limits shown above. Please contact your local AkzoNobel Aerospace Coatings representative to determine the proper application techniques when environmental conditions fall outside of the recommended range.



Equipment Recommendation
Air 1.4 mm nozzle orifice
HVLP 1.4 mm nozzle orifice
Airless 6.11 – 6.13, (.011 - .013 inch) angle 60°



Note Although electrostatic application of Aerodur Sealer 42240 is possible, the electrostatic effect may be minimal because of the high polarity of the mixed material.



Number of Coats Apply one closed cross coat or two single coats (viscosity 21 – 24 sec. ISO4), or apply one single coat, followed after 10 minutes flash off time by a cross-coat (viscosity 18 – 21 sec. ISO4).



Cleaning of Equipment Thinner 98066 followed by Solvent Cleaning C 28/15 or Solvent Cleaning 98068.



Note Thinner 98066 is not compatible with polyurethane products and intermix will lead to clogging of equipment.

The quality of the application of all coatings will be influenced by the spray equipment chosen and the temperature, humidity, and air flow of the paint application area. When applying the product for the first time, it is recommended that test panels be prepared in order to identify the best equipment settings to be used in optimizing the performance and appearance of the coating.

Physical Properties



Drying Times

23°C/73°F, 55% RH			
Dry to Tape	2 hours		
Recoatable Minimum	4 hours		
Recoatable Maximum	72 hours		
Overcoat window with Aerodur HS 2121 CF			
Temperature / RH	20 – 40%	41 – 60%	61 – 80%
15 – 20°C / 59 – 68°F	1 – 4 hrs	1 – 4 hrs	1 – 4 hrs
21 – 25°C / 69 – 77°F	1 – 3 hrs	1 – 3 hrs	1 – 3 hrs
26 – 30°C / 78 – 86°F	½ – 3 hrs	½ – 2 ½hrs	½ – 2 ½ hrs
31 – 35°C / 87 – 95°F	½ – 3 hrs	½ – 2 ¼ hrs	½ – 1 ¼ hrs
Overcoat window with Aerodur LV 2114			
Temperature / RH	Overcoat time		

Aerodur Sealer 42240

20°C / 68°F, 30 – 80%	2 – 4 hrs
25°C / 77°F, 20 – 70%	2 – 4 hrs
30°C / 86°F, 20 – 60%	2 – 3 ½ hrs
35°C / 95°F, 20 – 40%	2 – 3 hrs

Overcoat time Aerodur Sealer 42240 – Topcoat/Basecoat		
Temp.	Relative Humidity	Overcoat time
20°C-35°C / 68°F-86°F	20%-80%	4 – 72 hrs*
*) If efficient air movement is applied.		

Note:
If the recommended overcoat time of the primer is exceeded a fresh layer of the relevant primer must be applied according to the TDS in order to ensure optimal adhesion of the system.



Theoretical Coverage
12.5 m² per liter base at 8 µm dry film thickness.
562 ft² per US gallon base at 0.32 mil dry film thickness.



Dry Film Weight
2.0 g/m²/µm
0.010 lbs/ft²/mil



Gloss (60°)
Maximum 10 GU



Color
Off white



Flash Point	Aerodur® Sealer 42240	<21°C / 70°F
	Thinner 98066	<21°C / 70°F



Storage
Store the product dry and at a temperature between 5 and 35°C / 41 and 95°F per AkzoNobel Aerospace Coatings specification. Store in the original unopened containers. Storage temperature and shelf life may vary per OEM specification requirements. Refer to the container label for specific storage life information.

Shelf life 5 - 35°C (41 - 95°F)	Aerodur® Sealer 42240	12 months
	Thinner 98066	36 months

Safety Precautions
Comply with all local safety, disposal and transportation regulations. Check the Material Safety Data Sheet (MSDS) and label of the individual products carefully before using the products. The MSDS's are available on request.

Revision date: July 2026 (supersedes April 2023) - FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE
The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given is subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product. Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel